



Embroidery Service srl.
Via F.lli Bandiera 7
20090 Trezzano sul Naviglio - MI
Tel.0039.02.45898967
Cell.0039.339.4176273
Email: info@embroideryservice.it

DIGITAL ONE

DESCRIZIONE PRODOTTO

DIGITAL ONE è il nostro articolo economico in PVC con supporto in carta. Adatto a loghi medio/grandi prelevabili a mano ed a grosse scritte per lavori promozionali e sportivi utilizzando il nostro Application Tape.

TESSUTI

COTONE, POLIESTERE, TESSUTI MISTI

DATI TECNICI/TECHNICAL DATA

COMPOSIZIONE/COMPOSITION:	PVC/PU
SPESSORE/THICKNESS:	160 MICRONS
SUPPORTO/CARRIER:	CARTA NON ADESIVO/ PAPER WITHOUT ADHESIVE
FINITURA/COATING:	OPACA/MATT

TAGLIO/CUT

LAMA/BLADE:	STD 45° (LAMROL1005)
PRESSIONE/PRESSURE:	60/80 GF
DIMENSIONE MINIMA/MINIMUM SIZE:	3 CM
OFFSET:	0,250 MM

LAVAGGIO/WASHING

TEMPERATURA /TEMPERATURE	40°C DOPO 24 ORE AL ROVESCIO/AFTER 24 H INSIDE OUT
STIRO/IRON	DOPO 24 ORE AL ROVESCIO/AFTER 24 H INSIDE OUT
LAVAGGIO A SECCO/DRY WASHING	NO
CANDEGGINA O AGENTI CHIMICI/BLEACH OR CHEMICALS AGENTS	NO
ASCIUGATRICE/DRYER	NO

STOCCAGGIO MATERIALE

Consigliamo di non riporre i materiali alla luce solare diretta, in luoghi umidi o con temperature elevate.

CONSIGLI DI UTILIZZO

- Nella fase di SPELLICOLAMENTO, eliminare il materiale in eccesso tenendo la mano appoggiata al supporto per evitare il distaccamento di piccoli particolari.
- Nella fase di PRELIEVO della stampa consigliamo di utilizzare il nostro Application Tape e di prelevarla al rovescio girando il foglio di lavoro e rimuovendo il supporto, non l'Application Tape.
- Nella fase di APPLICAZIONE dopo aver pressato la stampa come da scheda tecnica consigliamo di rimuovere il supporto e ripressare la stampa per altri 5/10 secondi, coprendola con una carta siliconata, per assicurare una maggiore resistenza ai lavaggi.

• I seguenti dati tecnici sono i risultati dei nostri laboratori. Consigliamo, in ogni caso, di effettuare dei test prima di iniziare la produzione. Gli articoli da noi sviluppati possono subire variazioni al fine di essere migliorati. Il materiale può avere una variazione di spessore del + - 10%. Tale variazione non pregiudica la conformità del prodotto.

• The following technical data are the result of our laboratory test. We suggest, anyway, to do small trials before starting the industrial production. Our materials can be improved for better performance without any previous information. The product might have + - 10% thickness variation. It won't affect the performance.

PRODUCT DESCRIPTION

DIGITAL ONE is our cheap PVC material on a non adhesive paper. It can be used for big logos, numbers and for promotional jobs. You can pick it by hand. In case of promotional or sportwear big letterings the withdrawal is by our Application Tape.

FABRICS

COTTON, POLYESTER, BLENDED FABRICS

INDICAZIONI DI STAMPA/ PRINTING SETTINGS

PLOTTER:	ROLAND
PROFILO COLORE/COLOUR PROFILE:	TTRH
QUALITA' DI STAMPA/QUALITY OF PRINTING:	ALTA/HIGH
GESTIONE COLORE/COLOR MANAGEMENT:	MAX IMPACT
STAMPA-ASCIUGATURA/PRINTING-DRY TEMP	38°C/40°C

APPLICAZIONE/APPLICATION

TEMPERATURA/TEMPERATURE:	150°C
TEMPO/TIME:	10 SEC
RIMOZIONE SUPPORTO/REMOVE CARRIER:	A CALDO/HOT
PRESSIONE TERMOPRESSA MANUALE/PRESSURE MANUAL HEAT PRESS	MEDIA/MEDIUM
PRESSIONE TERMOPRESSA PNEUMATICA PNEUMATIC HEAT PRESS PRESSURE	3,5 BAR

APPLICATION TAPE

BLU/BLEU	
NEUTRO/CLEAR	

DIMENSIONI ROTOLI/ROLLS DIMENSIONS

L. ROLLS	25 Mtl
H ROLLS	Cm 50/75/100
Rotoli fuori misura disponibili previa vendita./ Short rolls available subject to prior sale.	

MATERIAL STORAGE

We suggest not to expose to direct sunlight and do not stock the materials in moist environment or high temperature warehouse.

INSTRUCTIONS

- During the PEELING phase, remove the material in excess by the hand on the support avoiding small details peel off.
- During the PICKING of the transfer we recommend our Application Tape and to turn the worksheet by removing the liner, not the Application Tape.
- During the APPLICATION, after having pressed the transfer as specified in the technical data sheet, we suggest to remove the support and to press the print again for another 5 or 10 seconds, covering it with silicon paper, in order to ensure a greater resistance to washing.